

Application No. 09/486,744

Page 2

Docket No. AD6530

Amendments to the Claims

Please amend Claims as indicated below:

1. (Currently Amended) A flexible or semi-flexible packaging material with an oxygen barrier between 10 and 100 cc/m²d atm as determined by ASTM 3985 and a water vapor barrier between 100 and 1000 g/m²d at 38°C and 90% relative humidity, as determined according to DIN 53122 issued July 1982, comprising

- (a) a layer of paper having a weight between 20 and 400 g/m² with layers applied thereto consisting essentially of
- (b) a layer of ethylene copolymer or grafted ethylene copolymer having a weight between 1 and 5 g/m² adjacent to and contacting layer (a), and
- (c) a layer of nylon comprising between 5 and 100 weight % of amorphous nylon and 0 and 95 weight % semicrystalline polyamide 6 having a weight between 10 and 30 g/m² adjacent to layer (b).

2. (Original) The packaging material of claim 1 wherein the ethylene copolymer of layer (b) is ethylene vinyl acetate, ethylene-ethyl acrylate, ethylene-methyl acrylate or ethylene butyl acrylate.

3. (Original) The packaging material of claim 1 wherein the ethylene copolymer of layer (b) is an ethylene-acid copolymer or its corresponding ionomer.

4. (Original) The packaging material of claim 1 wherein the grafted ethylene copolymer of layer (b) is a maleic anhydride grafted ethylene copolymer.

5. (Original) The packaging material of any one of claims 1 to 4 wherein layer (b) further comprises up to 40 weight % of a copolyether ester, a copolyether amide or a polyurethane thermoplastic.

6. (Previously presented) The packaging material of claim 5 which is produced by coextrusion coating layers (b) and (c) onto layer (a).

Application No. 09/486,744
Docket No. AD6530

Page 3

7. (Previously presented) The packaging material of claim 5 which is produced by lamination of extruded or coextruded layers (b) and (c) onto layer (a).

8. (Previously presented) A flexible or semi-flexible packaging material with an oxygen barrier between 10 and 100 cc/m²d atm as determined by ASTM 3985 and a water vapor barrier between 100 and 1000 g/m²d at 38°C and 90% relative humidity, as determined according to DIN 53122 issued July 1982, comprising

- (a) a layer of paper having a weight between 20 and 200 g/m² with layers applied thereto consisting essentially of
- (b) a layer of ethylene copolymer or grafted ethylene copolymer having a weight between 1 and 5 g/m² adjacent to and contacting layer (a), and
- (c) a layer of nylon comprising between 5 and 100 weight % of amorphous nylon and 0 and 95 weight % semicrystalline polyamide 6 having a weight between 10 and 30 g/m² adjacent to layer (b).

Application No. 09/486,744
Docket No. AD6530

Page 4

Respectfully submitted,



Craig H. Evans

Attorney for Applicant

Registration No. 31,825

Telephone: 302-992-3219

Facsimile: 302-992-3257

Dated: 4/16/2004